## Hydrous Kaolin (Powder) K99P (Paper Grade)

Edition: Rev H 25/05/2019

Chemical Property**	Value (%)
*SiO <sub>2</sub>	47.5
Al <sub>2</sub> O <sub>3</sub>	37.5
Fe₂O <sub>3</sub>	0.60
TiO <sub>2</sub>	0.40
K₂O	1.60
MgO	0.20
lg. Loss	12.0

Physical Property	Value
Fired ISO Brightness (%)	87.0
рН	6.8
Bulk Density (gm/cc)	0.6
Moisture content (%) by weight	1.0±1
Particle Size Distribution (Sedigraph %)	
Residue >45µm	1.0
<2µm	55

The above data are typical average data for the product and should not be treated as absolute specification.

**Country of Origin: Australia** 

<sup>\*</sup>Total Silica - could include traces of free silica.

<sup>\*\*</sup>XRF Analysis was performed by external service provider NAGROM Perth

<sup>\*\*\*</sup>Trace Element analyses also available on request.