

- **Taiwan Office:** 4F, 417-1, Chi Shyan 2nd Rd., Chyan Jin Dist., Kaohsiung, Taiwan  
TEL:(886) 7216-7357 FAX:(886) 7216-7356 <http://www.choko.asia/>
- **Hong Kong Office:** Flat 5, 31/F, Comweb Plaza, 12 Cheung Yue Street, Lai Chi Kok, Kowloon, HK  
TEL:(852) 2805-2425 FAX:(852) 3003-5459 <http://www.choko.asia/>

# NK8020


## Ceramics Grade

### 1. Chemical Analysis

SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O	Ig. Loss
67.40	22.50	0.13	0.11	0.04	0.25	0.18	4.49	4.10

**Moisture:** 35%±1%.

**Packing:** 1,000kg/bag; 20MTS/FCL.



**Country of Origin: Japan**